



Tennis Court



Paving Blocks



Basket Ball Court



City Park



Playground



propan
The Paint Specialist



Certificate ID03/0111



Certificate ID11/1102954057

www.propanraya.com

[f](#) Propan Raya ICC

[@propanraya](#)

08111 381 686

BC no.01/R2/TNK1000WA/OMP

propan
The Paint Specialist

TENNOKOTE®
THE ALL WEATHER SPORT COURT COATING



The only Indonesian sport court coating products with International Certification
INTERNATIONAL TENNIS FEDERATION
Reg. No : 01 / 02 - 17- L - CST - 536 - A

**NON SLIP COATING
FOR SPORT COURTS**



B01/TNK1000WA/09062022/OMP

TENNOKOTE TNK-1000 WA

THE ALL WEATHER SPORT COURT COATING

TENNOKOTE TNK - 1000 WA is a special coating for sport court, the only Indonesian product that is internationally certified, suitable for exterior and interior and have good adhesion for concrete, asphalt as well as paving block, so that can be used for city park, playground, side walk, car port, etc.

FEATURES

- ▶ **Water Based**
- ▶ **No Odor**
- ▶ **Good Adhesion**
- ▶ **UV Resistant**
- ▶ **Non Slip**
- ▶ **Quick Drying**
- ▶ **Free Mercury / Heavy Metal**
- ▶ **Easy to Apply**
- ▶ **12 Attractive Colors**



APPLICATION HINTS

1. The surface to be coated must be clean, dry and free from dust, grease and loose dirt.
2. Use grinder (Abrasive Cleaning), wire brush (manual or machine) if it is necessary add soap powder and rinse with clean water until it is really clean and then let it dry.
3. Stir TENNOKOTE thoroughly before applying.
4. Pour $\pm 10\%$ clean water (only when necessary), in to the mixture especially for the first / primer coat.
5. Apply 2-3 coats using brush or roller, allow 2 hours interval between coatings.
6. It is recommended applying TENNOKOTE in cross direction against the preceding coat for optimum result.
7. Protect the wet coat (within 2 hours of application) from rain, water and extreme temperature.
8. Do not apply under direct sunlight exposure or onto very hot surfaces.

NOTES:

1. If the paint is too condensed, thin sufficiently by water.
2. For the best result, do not apply in the rainy season, because **TENNOKOTE TENNIS COURT COATING TNK-1000 WA** can be dissolved by rainwater if it is not dried perfectly .
3. Do not apply under direct sunlight exposure.
4. Use the primer coal **TENNOKOTE SEALER TNK-1020 WA** to cover the pores from rough surfaces on courts made of asphalt.

PRODUCT DATA

■ Type	: Water based
■ Color	: As shown in the color card (12 attractive color)
■ Finish	: Matt
■ Solid by volume (mixture)	: 47%
■ Specific gravity (mixture)	: 1.20
■ Material consumption	: 1,5-2,0 m ² /kg (200 microns / three Coats included quartz sand)
■ Diluent	: Clean water
■ Recomended coating step	: I. 2 x coats include 10% quartz sand II. 1x coats top coat without sand.
■ Drying time	
Surface dry	: 10 minutes (30°C)
Hard dry	: 2 hours (30° C)
Ready to play	: 48 hours
■ Packaging	: 4.5 Kg & 22.5 kg (+ quartz sand 10 %)
■ Storage stability	: One year in original not opened boxes

Paints Required For Sport Court

Sport Courts	Courts Size	Courts Width	+ TENNOKOTE Paint Required
Tennis	10.97 x 23.78 m	260.86 m ²	6 Pail (6 x 25 kg)
BasketBall	28 x 15 m	420 m ²	9 Pail (9x 25 kg)
Futsal	25 x 15 m	375 m ²	8 Pail (8x 25 kg)
Volleyball	9 x 18 m	162 m ²	4 Pail (4x 25 kg)
Badminton	13.4 x 6.10 m	81.74 m ²	2 Pail (2x 25 kg)

Court Lines : $\pm 1 \times 5$ Kg, White / Yellow

Court Lines : Depending on the side court area
1 Kg of paint = 1.5 - 2.0 m²