



AQUA LASUR

DEEP PENETRATING WATERBASED EXTERIOR LASUR

APPLICATION DATA :

Recommended substrate	Exterior tropical hardwood
Recommended condition	25 - 35 ° C, 40 - 60 % RH
Dillution	Water if necessary (20% maximum)
Coating amount (Wet)	60 - 70 g/m ² percoat
Theoretical Coverage	10 m ² /kg mix at CA 60 g/m ² percoat
Drying time (30°C, RH = ± 50 %)	
- Dust free	15 - 20 minutes
- Tack free	60-120 minutes
- Hard Dry	180-240 minutes
Re-coating time	After 3-4 hours
Stacking time	16-17 hours



AQUA DECK LASUR

DURABLE EXTERIOR WOODEN FLOOR COATING

APPLICATION DATA :

Recommended substrate	Wooden floor (Hardwood)
Recommended condition	25 - 35 ° C, 40 - 60 % RH
Dillution	Water if necessary (20% maximum)
Coating amount (Wet)	60 - 70g/m ² percoat
Theoretical Coverage	10 m ² /kg mix at CA 60 g/m ² percoat
Drying time(30°C,RH= ±50%)	
- Dust free	15 - 20 minutes
- Tack free	60-120 minutes
- Hard Dry	180-240 minutes
Re-coating time	After 3-4 hours
Stacking time	16-17 hours

propan
The Paint Specialist



ULTRAN AQUA LASUR SERIES

THE BEST LASUR & WOOD STAIN
FOR TROPICAL CLIMATE

propan
The Paint Specialist



www.propanraya.com

Propan Raya ICC

@propanraya

08111 381 686

BOTAQUALASURSR/1100920/TON



ULTRAN AQUA LASUR AEL-505 is an environmentally friendly waterbased lasur for interior and exterior. This product penetrates deeply into the wooden pores that improves the stability of wood dimension.

ULTRAN AQUA LASUR AEL-505 specially designed for tropical climate & formulated to protect wooden parts of building from sunlight and rain, such as door, window frame, pergola, gazebo and also garden furniture.

ADVANTAGES

- Natural feel
- Fast Dry
- UV & Weather Resistant
- No brush mark
- Water repellent and Permeable
- Deep Penetrating
- Fungus and Mold resistant

ULTRAN AQUA LASUR AEL-505 has the same weather resistant level as Ultratan Lasur solvent based system. Ultratan Aqua Lasur has natural feel and high transparency. Apply **ULTRAN AQUA LASUR AEL-505** Clear Gloss / Dof as top coat for final step.

APPLICATION PROCEDURE

1. Sand along the wood grain with sandpaper number 180. For exterior usage, it is not recommended to apply wood filler as the primer of ULTRAN AQUA LASUR
2. Apply ULTRAN AQUA LASUR with brush and let 3 – 4 hours to dry. Sand lightly with sandpaper number 400. Repeat this step three times for optimum result.
3. For gloss/dof appearance, apply ULTRAN AQUA LASUR clear gloss/dof for final top coat (3rd coat).

- Tips :**
- Make sure the surface of wood is free from dirt before finishing.
 - Before recoating, wood needs sanding again with sandpaper no. 400 for better adhesion.
 - Do not apply wood filler to fill the pore for exterior uses, because the weather resistant and adhesion of Ultratan Aqua Lasur on the wood substrate will be affected.

USAGE OF ULTRAN AQUA LASUR AEL-505



Window



Door



Gazebo



Solid Wood Furniture



ULTRAN AQUA DECK LASUR ADL - 605 is an environmentally friendly water based lasur, specially designed for exterior wood flooring (deck). This product penetrates deeply into the wooden pore and improves the stability of wood dimension. Has a good weather and abrasion resistant, easy to use, flexible and no brush mark.

ADVANTAGES

- Abrasion resistant
- Environmentally Friendly
- Fast dry
- Natural feel
- UV & Weather Resistant
- No brush mark
- Water repellent and Permeable
- Deep Penetrating
- Fungus and Mold resistant

APPLICATION PROCEDURE

1. Sand the wood using sandpaper No. 180 along the wood grain
2. Apply ULTRAN AQUA DECK LASUR by brush and let to dry 3-4 hours. Sand lightly with sandpaper No. 400. Repeat this step twice.
3. Apply ULTRAN AQUA DECK LASUR as final top coat by brush.



TIPS FOR MAINTAIN YOUR WOODEN DECK

1. For new deck, make sure the deck is dry enough (moisture content of the wood should be less than 20%).
2. Don't takes too long to recoating, because the deck will dirtier and need heavy maintaining.
3. Coat all sides of the deck, horizontal side, vertical side and underneath the deck.
4. The climate and the traffic flow on the deck will makes the coating thinner, we recommend to coating the deck regularly every one or two years.
Don't wait until your deck lose the paint to recoating it, because this condition will damage your wood.

USAGE OF ULTRAN AQUA DECK LASUR ADL - 605



Wooden Pool Deck



Wooden Park Deck



Wooden Terrace Deck